

PRODUCT SPECIFICATION SHEET CRUSHED GRANITE (GRAVEL) 19 - 25 mm

Crushed Granite from Apoera conform the ASTM and NEN-EN



Baitali Mining N.V.

Duisburglaan 29, Paramaribo, SA, Suriname

(597) 53 06 54 Fax: (597) 53 06 57

www.baitaligroup.com



GRADING SPECIFICATION CONFORM THE ASTM C 136

<i>Sieve No.</i>	<i>Sieve Size [mm]</i>	<i>19 - 25 mm</i>	<i>Grading limits [%]</i>
2"	50	100	
1½"	37.5	100	
1¼"	31.5	100	100
1"	25	99	90 - 100
¾"	19	20	20 - 55
½"	12.5	1	0 - 10
⅜"	9.5	1	0 - 5
No. 4	4.75	1	
No. 8	2.36	0	
No. 16	1.18	0	
No. 30	0.6	0	
No. 50	0.3	0	
No. 100	0.15	0.2	
No. 200	0.075		
< No. 200			

MATERIAL PROPERTIES

<i>Type of test</i>	<i>Standard</i>	<i>Limit value</i>	<i>Test result</i>
Flakiness index	NEN-EN 933-3	≤ 45%	34%
Los Angeles Abrasion	ASTM C131	< 30%	23%
Water absorption	ASTM C127	< 2%	0.50%
Specific Gravity (OD)	ASTM C127		2.70
Specific Gravity (SSD)	ASTM C127		2.71
Apparent Specific Gravity	ASTM C127		2.72
Loose Bulk Density	NEN-EN 1097-3		1380 kg/m ³

Material tested by:

Baitali Pavement Testing & Technologies N.V., ISO certified laboratory

