

PRODUCT SPECIFICATION SHEET CRUSHED GRANITE (Waste) 0 - 6 mm

Crushed Granite from Apoera conform the ASTM and NEN-EN



Baitali Mining N.V.

Duisburglaan 29, Paramaribo, SA, Suriname

(597) 53 06 54 Fax: (597) 53 06 57

www.baitaligroup.com



GRADING SPECIFICATION CONFORM THE ASTM C 136

<i>Sieve No.</i>	<i>Sieve Size [mm]</i>	<i>Waste</i>	<i>Grading limits [%]</i>
2"	50		
1½"	37.5		
1¼"	31.5		
1"	25		
¾"	19		
½"	12.5		
⅜"	9.5	100	100
No. 4	4.75	97	93 - 98
No. 8	2.36	68	47 - 76
No. 16	1.18	42	26 - 54
No. 30	0.6	24	14 - 36
No. 50	0.3	14	8 - 24
No. 100	0.15	7	5 - 14
No. 200	0.075	4.0	2.6 - 7.3
< No. 200			

MATERIAL PROPERTIES

<i>Type of test</i>	<i>Standard</i>	<i>Limit value</i>	<i>Test result</i>
Water absorption	ASTM C127		2.30%
Specific Gravity (OD)	ASTM C127		2.58
Specific Gravity (SSD)	ASTM C127		2.64
Apparent Specific Gravity	ASTM C127		2.74
Sand Equivalent	ASTM 2419	> 45%	67%
Loose Bulk Density	NEN-EN 1097-3		1530 kg/m ³

Material tested by:

Baitali Pavement Testing & Technologies N.V., ISO certified laboratory

